

Innovative Biochar Applications for Sustainable Water Purification

An Mariya Deve M D¹

Department of Civil Engineering
Amal Jyothi College of Engineering
Kanjirapally, India
anmariyadevemd2023@ce.ajce.in

Aswani Unni¹

Department of Civil Engineering
Amal Jyothi College of Engineering
Kanjirapally, India
aswaniunni2023@ce.ajce.in

Bhagya S¹

Department of Civil Engineering
Amal Jyothi College of Engineering
Kanjirapally, India
bhagyas2023@ce.ajce.in

Abin Joseph¹

Department of Civil Engineering
Amal Jyothi College of Engineering
Kanjirapally, India
abinjoseph2023@ce.ajce.in

Dr. Aju Mathew George²

Department of Civil Engineering
Amal Jyothi College of Engineering
Kanjirapally, India
ajumathewgeorge@amaljyothi.ac.in

Abstract—The modern world's increasingly developed industries have significantly polluted the planet on which we live. The water resources, on which human existence depends, are being gravely compromised and degraded due to pollution. Currently, it is imperative that we address the issue of water pollution. In the process of treating water, new materials are constantly being used in an effort to achieve sustainable development. Biochar material is one of them. During the thermochemical method, biofuel generates a by-product known as coke or biochar through the breakdown of the biofuel source. With its affordability and expansive specific surface area this substance offers numerous advantages and uses in catalysis, fuel cell technology, adsorption, enhancing soil quality, along with a significant potential for widespread application. As a result, biochar has emerged as a method for increasing thermochemical processes' efficiency and monetary benefits in water treatment. This summary initially covers the techniques utilized in producing novel biomass materials. It then organizes and evaluates various approaches to modifying them before delving into the possible utilization of biochar substances in addressing wastewater concerns. Water treatment, bio-char, adsorption, sustainable development, biomass

Keywords—Water treatment; bio-char; adsorption; sustainable development; biomass

I. INTRODUCTION

The world we live in today is exposed to huge amounts of pollutants which are released from many industries. Water bodies have been seriously affected by pollution. The main

water pollutants are bacteria, viruses, parasites, fertilizers, pesticides, drugs, nitrates, phosphates, plastics and even radioactive substances. The world is focusing on sustainable development and proposing many suggestions for the sustainable treatment of water in order to reduce carbon dioxide emissions, secondary pollution and consumption. In this scenario, biochar material is introduced. It is obtained from plant and animal biomass which is low pollution and economic material.

Biomass consists mainly of cellulose, hemicellulose and lignin. Most of the hemicellulose and some of the cellulose are broken down during torrefaction up to about 300 °C. Biochar can be used in many applications, from heat and power generation to soil remediation [41]. The properties of bio-char depend on the raw material and process conditions. Choosing suitable conditions for the production of biochar with the desired properties therefore requires proficiency on dependencies and influencing factors, both quantitatively and qualitatively. Biochar is a solid product of biomass pyrolysis. The amount of product obtained from the pyrolysis of a given biomass depends on process conditions such as temperature and residence time. [40].

Physical pretreatment technology usually involves drying, crushing, screening and washing of biomass. The lignocellulosic raw material/plant is usually dried to a standard weight at 105°C or other temperature, ground with a hammer mill into smaller particles and then cut into different pieces. Chemical pretreatment technology often relies on chemical

reactions for conversion characteristics or composition of the raw material. One of the most commonly used chemicals pretreatment technology is the treatment of biomass raw materials with chemicals or functional substances materials for loading chemical precursors or functional substances into raw materials.

Thermal processes to convert biomass into biochar mainly include pyrolysis, hydrothermal carbonization, gasification and microwave pyrolysis. Pyrolysis is a thermochemical process for breaking down biomass under anoxic or hypoxic conditions to the environment. Pyrolysis processes depend on the operating temperature, heating velocity and residence time used, which can affect compositions and physicochemical properties of products [41].

II. MECHANISM OF PREPARATION OF BIOCHAR MATERIALS FOR WATER TREATMENT

An organic material such as wood, agricultural waste, or animal dung is heated without oxygen to create biochar, a type of charcoal. A highly porous substance with a substantial surface area and the ability to absorb contaminants from water, biochar is a promising candidate for environmentally friendly water treatment [38]. The following steps are necessary to prepare biochar materials for sustainable water treatment:

Raw material selection: Picking out the raw materials is the first step in making biochar materials for water treatment[39]. The features of the biochar, such as its porosity, surface area, and adsorption capacity, can be impacted by the choice of source material. Rice husks, sawdust, wood chips, and coconut shells are typical raw materials used in the manufacturing of biochar.

Pyrolysis: To create biochar, the basic ingredients are pyrolyzed in the second stage. The raw materials are heated at temperatures between 400°C and 800°C during the pyrolysis process without the presence of oxygen[35]. A very porous solid material is left behind after the heating process causes the organic ingredients to disintegrate and release gases.

Activation: The biochar is activated in the third step to increase its capacity for adsorption. In order to build more holes and enhance the biochar's surface area, activation entails subjecting the material to an oxidizing agent like steam, air, or chemicals like potassium hydroxide.

Due to its high porosity and adsorption capacity, biochar is a promising material for sustainable water treatment. But, by using modification methods, the performance of biochar can be further improved. Many strategies are involved in the alteration of biochar materials for sustainable water treatment:

Chemical modification - entails subjecting the biochar material to chemical agents, such as acids, bases, and oxidising agents, in order to change its surface chemistry and improve its ability to adsorb particular pollutants[37]. For instance, it has been demonstrated that biochar may be

modified with citric acid to increase its capacity to adsorb heavy metals, and that it can be modified with hydrochloric acid to increase its capacity to adsorb organic contaminants.

Physical modification: To improve the surface area and pore size distribution of the biochar material, physical modification entails changing the structure of the biochar substance[34]. Steam activation, microwave treatment, and ball milling are examples of physical alteration procedures. With the use of these methods, the biochar's surface area and number of pores can be increased, which improves the biochar's ability to absorb contaminants.

Biological modification: Biological modification entails modifying the biochar material using microorganisms like bacteria or fungi. These bacteria can attach to the charcoal surface and release extracellular enzymes that alter the surface chemistry of the biochar and increase its ability to adsorb particular pollutants [33].

Activated carbon, zeolites, or clay minerals are some examples of additional elements that can be combined with biochar to generate a composite material with improved adsorption capacity for contaminants. Adding biochar to other materials can have synergistic effects that increase its ability to adsorb pollutants and increase its selectivity for particular contaminants.

Surface functionalization includes adding functional groups, such as carboxyl, hydroxyl, or amino groups, to the surface of the biochar material in order to increase its ability to adsorb particular pollutants. Either biological or chemical alteration can be used to implement this strategy[36].

Overall, the adsorption capability, selectivity, and durability of biochar materials for sustainable water treatment can be improved. Depending on the specific application and the kind of contaminants that need to be removed from water, a modification strategy is chosen.

A. CHEMICAL ALTERATION

Acid treatment: To produce carboxylic and phenolic functional groups on the surface of the biochar material, powerful acids such as sulfuric acid or hydrochloric acid are used to treat the biochar material. This modification method raises the surface charge and enhances the ability of contaminants, such as heavy metals, which are positively charged, to be absorbed.

Base treatment: To produce hydroxyl and amino functional groups on the surface of the biochar material, the biochar material is treated with strong bases like sodium hydroxide or potassium hydroxide[39]. This modification method raises the surface charge and enhances the ability of negatively charged contaminants, such as organic molecules, to be adsorbent.

Oxidation - Treatment using oxidising chemicals, such as hydrogen peroxide or potassium permanganate, to produce carboxylic and carbonyl functional groups on the surface of

the charcoal material is known as oxidation. This modification method boosts the surface charge and enhances the ability of contaminants like phenols and dyes to be absorbed by the material.

Silane treatment: Silane treatment entails adding organosilane functional groups to the surface of the biochar material by treating it with organosilanes like trimethylchlorosilane or tetraethoxysilane. During this modification process, a hydrophobic surface is produced, improving the adsorption capability for non-polar contaminants like hydrophobic organic molecules[35].

Chelation treatment entails treating the charcoal material with chelating substances like citric acid or ethylenediaminetetraacetic acid (EDTA) to produce chelating functional groups on the surface. By creating compounds with metal ions, this modification method boosts the capacity for heavy metal adsorption.

In general, the sort of chemical modification technique chosen relies on the application in question as well as the kind of pollutants that need to be eliminated from the water. The selectivity and adsorption capability of biochar materials for environmentally friendly water treatment applications can be greatly increased through chemical modification[34].

Another typical technique for surface modification of biochar materials for environmentally friendly water treatment is physical modification. In order to boost the biochar material's adsorption capacity and selectivity towards particular contaminants, it must be treated physically to create new pores, increase surface area, and improve accessibility of adsorption sites.

B. PHYSICAL MODIFICATION TECHNIQUE

Pyrolysis therapy - Pyrolysis is a process that includes heating up biochar material at a high temperature in an oxygen-free environment. This process enhances the biochar's surface area and develops new pores [33]. The adsorption capacity for several contaminants, including organic compounds, heavy metals, and nutrients, is increased thanks to this modification process, which also increases the accessibility of adsorption sites.

Treatment for activation: The biochar material is subjected to an activation procedure that involves heating it to a high temperature and adding activators, such as steam or carbon dioxide, to expand the biochar's surface area and produce new pores. Using this modification process, adsorption sites are made more accessible and numerous contaminants, including heavy metals, organic compounds, and nutrients, are able to bind to them more effectively.

Using a microwave to irradiate the biochar material results in the formation of new pores and an increase in the biochar's

surface area [34]. Using this modification process, adsorption sites are made more accessible and numerous contaminants, including heavy metals, organic compounds, and nutrients, are able to bind to them more effectively.

Ultrasound treatment: Ultrasonic waves are used to treat the biochar material, causing it to develop new pores and increase its surface area. This modification method raises the accessibility of adsorption sites and increases the ability of numerous contaminants, including heavy metals, organic molecules, and nutrients, to adsorb.

Mechanochemical treatment: Mechanochemical treatment involves applying mechanical pressure to the biochar material, such as milling or grinding, to increase the surface area and generate new pores [36]. This modification method raises the accessibility of adsorption sites and increases the ability of numerous contaminants, including heavy metals, organic molecules, and nutrients, to adsorb.

In general, the physical modification technique selected relies on the particular application and the kind of pollutants that need to be eliminated from the water. The selectivity and adsorption capability of biochar materials for environmentally friendly water treatment applications can be greatly improved through physical modification.

For surface modification of biochar materials for environmentally friendly water treatment, biological modification is a less popular technique. It entails treating the biochar material with microbes or enzymes to add new functional groups to its surface or change the current functional groups, which improves the material's ability to adsorb pollutants and increase its selectivity for particular pollutants[37].

C. BIOLOGICAL MODIFICATION TECHNIQUE

Treatment for microbes - The term "microbial treatment" refers to the process of modifying the surface chemistry of biochar by adding microorganisms, such as bacteria or fungi, to the biochar material. In order to increase the adsorption capacity and selectivity for particular pollutants, this modification process can either introduce new functional groups, like carboxylic and phenolic groups, or change the current functional groups.

Enzymatic treatment - entails exposing the biochar material to enzymes, such as peroxidases or laccases, that can oxidise or decrease the surface functional groups of the biochar material. The adsorption capacity and selectivity for particular contaminants are increased by using this modification process, which can add new functional groups or change the current functional groups[38].

Treatment by bioaugmentation - To increase the adsorption capacity and selectivity for particular pollutants, bioaugmentation includes adding microorganisms or enzymes to the polluted water or soil together with the charcoal material. This method of modification can enhance the biodegradation and adsorption of contaminants, such as organic substances, heavy metals, and nutrients [20]. Biological modification can, in general, offer a sustainable and environmentally beneficial way for surface modification of biochar materials for sustainable water treatment. However, the application of biological modification approaches necessitates careful evaluation of the microbial or enzymatic activity, compatibility with the biochar material, and potential interactions with the pollutants and environment [12].

Another technique for surface modification of biochar materials for environmentally friendly water treatment is composite modification. The biochar material is combined with other substances, such as polymers or nanoparticles, to form a composite substance with improved adsorption and selectivity towards particular contaminants[35]. There are several different kinds of composite alteration methods that can be applied, including:

Combination of polymers: In order to generate a composite material with improved adsorption capacity and selectivity for particular contaminants, including heavy metals, dyes, or organic compounds, polymer composite modification entails mixing charcoal material with a polymer, like chitosan or polyvinyl alcohol. Additional functional groups from the polymer, like amino or hydroxyl groups, can increase the biochar material's potential for adsorption and selectivity.

D. SURFACE MODIFICATION TECHNIQUE

Nanoparticle composite: The modification of nanoparticle composites involves combining the biochar material with nanoparticles, such as iron oxide or silver nanoparticles, to produce a composite material that has improved adsorption capacity and selectivity for particular pollutants, such as heavy metals or organic compounds [12]. The nanoparticles may offer more active sites or catalytic qualities that raise the biochar material's ability for adsorption and selectivity.

Carbon composite: In order to modify a carbon composite, the biochar material must be combined with carbon-based substances like graphene or carbon nanotubes. This creates a composite material with improved adsorption capacity and selectivity for particular pollutants, like organic compounds or dyes [20]. The carbon-based compounds might offer more active sites or catalytic qualities that would improve the biochar material's capacity for adsorption and selectivity.

Metal oxide composite: To modify a metal oxide composite, combine biochar with metal oxide particles, such titanium dioxide or zinc oxide, to produce a composite

material with improved adsorption capacity and selectivity for particular contaminants, including organic chemicals or colours[25]. The additional active sites or catalytic qualities that the metal oxide particles can offer can improve the biochar material's selectivity and adsorption capability [10].

The overall adsorption capacity and selectivity of biochar materials for sustainable water treatment applications can be greatly increased through composite modification. The kind of contaminants to be removed from the water and the specific application determine the composite material to be used[27]. Moreover, composite modification can improve the stability and reusability of the biochar material, among other advantages.

III. PRODUCTION OF BIOCHAR

Notably, two of the key factors affecting the economical and effective manufacturing of biochar are the availability of feedstock and its composition. These include aquatic and woody biomass, municipal trash, paper waste, and agricultural biomass [27]. The most widely employed agricultural wastes in the manufacturing of biochar are rice straw, cotton stalk, and coconut shell. The two types of municipal waste that are most frequently utilized as feedstocks for the manufacture of biochar are sewage sludge and papermill sludge. Woody biomass includes materials like pine sawdust and used wood chips, while aquatic biomass like seaweed and Macroalgae sp. is frequently used as a feedstock for the creation of biochar [28].

The traditional way to make biochar is to pile it up in dirt pits and let it burn slowly with little to no airflow[29]. Another approach involved burning the biomass outdoors and immediately covering the partially burned biomass with soil [30]. Pyrolysis is the name given to this process. Pyrolysis is a method of thermal degradation that excludes oxygen from the process while using heat to break down biomass [2]. Traditional approaches use slow and quick pyrolysis as methodologies.

The chosen biomass is fully dried before being ground into biochar. The pulverized materials were then processed to the next-smallest size of 40 mesh [11]. Biomass must be heated at a rate of 5 to 7°C per minute for at least more than 24 hours in order to accomplish slow pyrolysis. A continuous auger/screw pyrolyzer reactor is typically used to carry out the slow pyrolysis process [3]. As a result, syngas (20–30%), bio-oil (25–35%), and biochar (35–45%) are all key products produced [3]. The process of fast pyrolysis is carried out in the absence of oxygen at a temperature more than 500°C and a heating rate greater than 300°C per minute [31]. Fast pyrolysis is primarily used to produce biochar on a large scale.

IV. APPLICATION OF BIOCHAR IN WASTEWATER TREATMENT

As our demand on the environment continues to grow, many pollutants with low concentrations but significant environmental harm are gradually gaining attention. Environmentally dispersed industrial sewage has been linked to human carcinogenicity, toxicity, mutagenicity, and teratogenicity [16]. Despite the fact that there are numerous methods for treating wastewater, five in particular are frequently employed: adsorption [17], chemical precipitation, membrane separation, built wetlands, and ion exchange. However, some of these technologies have a number of disadvantages, such as the difficulty of the process, high operating and maintenance costs, inefficiency in removing pollutants at low concentrations, inability to transform contaminants into biodegradable or less harmful by-products, and excessive energy and chemical use [16].

The primary treatment method is adsorption since it is flexible and efficient. In the study of adsorption, biochar is receiving special interest from researchers because of its enormous specific surface area and functional divisions [4]. To increase the effectiveness of adsorption, biochar's surface characteristics can be modified. Another significant aspect of biochar that adds to its attractiveness is its low price. One factor that contributes to biochar's low price is that it is made mostly from agricultural and solid waste. In another study, modified biochar's cost was discovered to be over half that of activated carbon, and its adsorption capacity was demonstrated to be almost identical [10].

The effectiveness of biochar in removing organic debris, surfactants, and nitrogen (N) from wastewater has been demonstrated in earlier studies. When treating wastewater, biochar can be used effectively as a phosphorus (P) sorbent. The sorbent then produced various products (phosphorus fertilizers) using a recycling technique, which is well known for its capacity to enhance soil quality [9]. Chemical pollutants known as micropollutants pose a threat to both the environment and human health. Extremely complex chemical molecules known as micropollutants are primarily found in water [9]. The most prevalent sources of micropollutants are pharmaceuticals, antibiotics, cosmetics and toiletries, endocrines, organic contaminants with a long half-life cycle, disinfection by-products, and other industrial chemicals [9]. These micropollutants are persistent and long-lasting in the environment, and they can be found in a range of settings. The majority of micropollutants are found in water in incredibly small concentrations, but because they can accumulate in creatures at every stage of the food chain, they can still have a negative impact on human health and the environment [12]. Antibiotics like tetracycline, doxycycline, and clindamycin, personal care items like triclosan [6], analgesics like ibuprofen and carbamazepine [5], and psychoactive substances like caffeine [6] are some of the micropollutants that can be discovered in water bodies. Long-term studies have been

conducted on the use of modified biochar to remove tetracycline and other micropollutants from water.

Recent research has demonstrated the efficiency of biochar in the removal of inorganic contaminants from wastewater, including heavy metals. Among the contaminants that might be discovered in wastewater are heavy metals. It can build up in creatures, endangering the wellbeing of other members of the food chain, particularly humans.

Dye pollutants in aqueous solutions are the main cause for worry. Chromium (Cr) removal using biochar made from bio-oil has already been studied [7]. In the industrial, compounds containing hexavalent chromium Cr(VI) are frequently utilized as dye pigments [8]. It has been demonstrated that the biochar-based adsorbents have a high capacity for adsorbing this substance [8]. Biochar has been touted as a good way to remove methyl violet from wastewater, which has been anticipated to be a possible adsorbent [8].

V. CONCLUSION

The development of new biochar materials has emerged as an exciting area of research in recent years, particularly in the field of wastewater treatment. This has led to significant improvements in efficiency and cost reduction, aligning with the principles of sustainable development. However, it is crucial to evaluate the toxicity of biochar and the environmental impact of chemicals used in its preparation to avoid the risk of secondary pollution. Although immersion in metal solutions is the most common method of biochar modification, exploring new preparation methods, such as microwave activation and hydrothermal carbonization, could add more functionality to biochar materials. Furthermore, it is essential to develop new catalysts that are recyclable, low-cost, and environmentally friendly for environmental pollution control projects. Finally, investigating new uses and functions of biochar materials could lead to further cost and emission reduction in the future.

Acknowledgment

The authors would like to thank the editors for this valuable comments and suggestions that improved the quality of the paper.

References

- [1] Enders, A.; Hanley, K.; Whitman, T.; Joseph, S.; Lehmann, J. Characterization of biochars to evaluate recalcitrance and agronomic performance. *Bioresour Technol* 2012, 114, 644–653.
- [2] Basu, P. Pyrolysis and Torrefaction. In: *Biomass gasification and pyrolysis: practical design and theory*. Academic Press: Burlington, USA, 2010; pp. 65–96

- [3] Verma, M.; Godbout, S.; Brar, S.K.; Solomatnikova, O.; Lemay, S.P.; Larouche, J.P. Biofuels production from biomass by thermochemical conversion technologies. *Int J Chem Eng* 2012, 1–18
- [4] Bu, J.B.; Wenyu, L.; Ning, N.; Ning, G.; Hao, Z.; Cheng, C.; Ding, A. Adsorption of Cr(VI) from wastewater by iron-modified coconut shell biochar. *E3S Web Conf* 2021, 248.
- [5] Nieto, A.; Borrull, F.; Pocurull, E.; Marcé, R.M. Occurrence of pharmaceuticals and hormones in sewage sludge. *Environ Toxicol Chem* 2010, 29, 1484–1489
- [6] Subedi, B.; Lee, S.; Moon, H.-B.; Kannan, K. Emission of artificial sweeteners, select pharmaceuticals, and personal care products through sewage sludge from wastewater treatment plants in Korea. *Environ Int* 2014, 68, 33–40
- [7] Mohan, D.; Rajput, S.; Singh, V.K.; Steele, P.H.; Pittman, C.U. Modeling and evaluation of chromium remediation from water using low cost bio-char, a green adsorbent. *J Hazard Mater* 2011, 188, 319–333
- [8] Li, Z.; Tang, Q.; Katsumi, T.; Tang, X.; Inui, T.; Imaizumi, S. Leaf char: an alternative adsorbent for Cr(III). *Desalination* 2010, 264, 70–77
- [9] Kopecký, M.; Kolář, L.; Konvalina, P.; Strunecký, O.; Teodorescu, F.; Mráz, P.; Peterka, J.; Váchalová, R.; Bernas, J.; Bartoš, P.; Filipov, F.; Bucur, D. Modified biochar-a tool for wastewater treatment. *Energies* 2020, 13
- [10] Fdez-Sanroman, A.; Pazos, M.; Rosales, E.; Sanroman, M.A. Unravelling the environmental application of biochar as low-cost biosorbent: a review. *Appl Sci* 2020, 10
- [11] Rambli, J.; Ghani, W.A.W.A.K.; Salleh, M.A.M. Characterization of sago-based biochar feedstock for solid fuel. *Journal of Energy and Safety Technology* 2018, 1, 11–17
- [12] Gomes, A.R.; Justino, C.; Rocha-Santos, T.; Freitas, A.C.; Duarte, A.C.; Pereira, R. Review of the ecotoxicological effects of emerging contaminants to soil biota. *J Environ Sci Health - Part A Toxic/Hazard Subst Environ Eng* 2017, 52, 992–1007
- [13] Cantrell, K.B.; Hunt, P.G.; Uchimiya, M.; Novak, J.M.; Ro, K.S. Impact of pyrolysis temperature and manure source on physicochemical characteristics of biochar. *Bioresour Technol* 2012, 107, 419–428
- [14] Lehmann, J.; Joseph, S. Biochar for environmental management: an introduction. In: *Biochar for Environmental Management Science and Technology*. First edition.; Lehmann, J.; Joseph, S. Eds.; Earthscan: London, UK, Volume 1, 2009; pp. 1–9
- [15] Liu, Z.; Zhang, F.S.; Wu, J. Characterization and application of chars produced from pinewood pyrolysis and hydrothermal treatment. *Fuel* 2010, 89, 510–514
- [16] Goltz, M.N.; Gandhi, R.K.; Gorelick, S.M.; Hopkins, G.D.; Smith, L.H.; Timmins, B.H.; McCarty, P.L. Field evaluation of in situ source reduction of trichloroethylene in groundwater using bioenhanced in-well vapor stripping. *Environ Sci Technol* 2005, 39, 8963–8970
- [17] Catizzone, E.; Sposato, C.; Romanelli, A.; Barisano, D.; Cornacchia, G.; Marsico, L.; Cozza, D.; Migliori, M. Purification of wastewater from biomass-derived syngas scrubber using biochar and activated carbons. *Int J Environ Res Public Health* 2021, 18, 4247
- [18] Cheng, Z.; Fu, F.; Dionysiou, D.D.; Tang, B. Adsorption, oxidation, and reduction behavior of arsenic in the removal of aqueous As(III) by mesoporous Fe/Al bimetallic particles. *Water Res* 2016, 96, 22–31
- [19] Fu, F.; Wang, Q. Removal of heavy metal ions from wastewaters: a review. *J Environ Manage* 2011, 92, 407–418, <https://doi.org/10.1016/j.jenvman.2010.11.011>.
- [20] Ahmad, J.; Patuzzi, F.; Rashid, U.; Shahabz, M.; Ngamcharussrivichai, C.; Baratieri, M. Exploring untapped effect of process conditions on biochar characteristics and applications. *Environ Technol Innov* 2020, 21
- [21] Demirbas, A.; Arin, G. An overview of biomass pyrolysis. *Energy Source* 2002, 24, 471–482
- [22] Mohan, D.; Pittman, C.U.; Steele, P.H. Pyrolysis of wood/biomass for bio-oil: a critical review. *Energy Fuels* 2006, 20, 848–889
- [23] Brown, R., *Biochar Production Technology*. In: *Biochar for Environmental Management: Science and Technology*. First Edition.; Lehmann, J.; Joseph, S. Eds.; Earthscan: London, UK, 2009; pp. 127–139
- [24] Karaosmanoglu, F.; Işığür-Ergüdenler, A.; Sever, A. Biochar from the straw-stalk of rapeseed plant. *Energy Fuels* 2000, 14, 336–339
- [25] Uchimiya, M.; Klasson, K.T.; Wartelle, L.H.; Lima, I.M. Influence of soil properties on heavy metal sequestration by biochar amendment: 1. Copper sorption isotherms and the release of cations. *Chemosphere* 2011, 82, 1431–1437
- [26] Lian, F.; Huang, F.; Chen, W.; Xing, B.; Zhu, L. Sorption of apolar and polar organic contaminants by waste tire rubber and its chars in single- and bi-solute systems. *Environ Pollut* 2011, 159, 850–857
- [27] Gabhane, J.W.; Bhange, V.P.; Patil, P.D.; Bankar, S.T.; Kumar, S. Recent trends in biochar production methods and its application as a soil health conditioner: a review. *SN Applied Sciences* 2020, 2
- [28] Roberts, D.A.; Cole, A.J.; Paul, N.A.; de-Nys, R. Algal biochar enhances the re-vegetation of stockpiled mine soils with native grass. *J Environ Manage* 2015, 161, 173–180
- [29] Barrow, C.J. Biochar: potential for countering land degradation and for improving agriculture. *Appl Geogr* 2012, 34, 21–28, <https://doi.org/10.1016/j.apgeog.2011.09.008>.
- [30] Emrich, W. Traditional methods of the smallholder charcoal-maker. In: *Handbook of Charcoal Making*. Emrich, W. Eds.; Springer, Dordrecht, Netherlands, Volume 7, 2013; pp. 19–104
- [31] Dai, L.; Fan, L.; Liu, Y.; Ruan, R.; Wang, Y.; Zhou, Y.; Zhao, Y.; Yu, Z. Production of bio-oil and biochar from soapstock via microwave-assisted co-catalytic fast pyrolysis. *Bioresour Technol* 2017, 225, 1–8
- [32] Kong, S.-H. et al. (2014). Bio-char from oil palm biomass: A review of its potential and challenges. *Renewable and Sustainable Energy Reviews*, 39, pp.729–739
- [33] Padzil, Farah Nadia Mohammad, et al. “Potential of Oil Palm Empty Fruit Bunch Resources in Nanocellulose Hydrogel Production for Versatile Applications: A Review.” *Materials*, vol. 13, no. 5, Mar. 2020, p. 1245
- [34] Salleh, K.M.; Zakaria, S.; Sajab, M.S.; Gan, S.; Kaco, H. Superabsorbent hydrogel from oil palm empty fruit bunch cellulose and sodium carboxymethylcellulose. *Int. J. Biol. Macromol.* 2019, 131, 50–59.
- [35] Xu, Z.; Li, J.; Zhou, H.; Jiang, X.; Yang, C.; Wang, F.; Pan, Y.; Li, N.; Li, X.; Shi, L.; et al. Morphological and swelling behavior of cellulose nanofiber (CNF)/poly(vinyl alcohol) (PVA) hydrogels: Poly(ethylene glycol) (PEG) as porogen. *RSC Adv.* 2016, 6, 43626–43633.
- [36] Basri, Nor Afifah, et al. “Malaysia Energy Strategy towards Sustainability: A Panoramic Overview of the Benefits and Challenges.” *Renewable and Sustainable Energy Reviews*, vol.42, Feb. 2015, pp. 1094–105.
- [37] Basri, Nor Afifah, et al. “Malaysia Energy Strategy towards Sustainability: A Panoramic Overview of the Benefits and Challenges.” *Renewable and Sustainable Energy Reviews*, vol.42, Feb. 2015, pp. 1094–105.
- [38] Wang, Shurong, et al. “Influence of the Interaction of Components on the Pyrolysis Behavior of Biomass.” *Journal of Analytical and Applied Pyrolysis*, vol. 91, no. 1, May 2011, pp. 183–89.
- [39] Selvarajoo, Anurita, et al. “An Experimental and Modelling Approach to Produce Biochar from Banana Peels through Pyrolysis as Potential Renewable Energy Resources.” *Modeling Earth Systems and Environment*, vol. 6, no. 1, Mar. 2020, pp. 115–28.
- [40] Weber, K., and P. Quicker. 2018. “Properties of biochar.” *Fuel*, 217: 240–261.

- [41] Xiang, W., X. Zhang, J. Chen, W. Zou, F. He, X. Hu, D. C. W. Tsang, Y. S. Ok, and B. Gao. 2020. "Biochar technology in wastewater treatment: A critical review." *Chemosphere*, 252: 126539.